



# Technical Datasheet

## Q 20-300 2K Polyester Multi Putty

### Characteristics:

2K Polyester Multi Putty is a multifunctional polyester putty, designed for steel, aluminium, galvanized surfaces and polyester laminates. Due to its excellent thixotropy it has very good shaping properties in any required thickness. It can also be used as a finishing putty, leaving a smooth surface without pores. For filling unevennesses especially on aluminium and galvanized surfaces. Destined for manual / machine treatment with sanding dry materials. For very large unevenness putty should be applied in several layers. Does not fill sandpaper while grinding.

### Application:

The surface must be clean, dry, degreased and matted. Thoroughly mix putty and 2-3% of hardener BPO by weight. Apply within 5 minutes at 20°C. Higher temperature can reduce the pot life and accelerates the drying time.

### Note:

Using too much hardener can lead to topcoat discoloration. It is not recommended to use putty below 15°C.

### Technical data:

Density: 1,84 - 1,86 g/cm<sup>3</sup>


Colour: beige



2004/42/II(b)(250)<250




Cleaning  
60-010



BPO- 2-3%




Pot life  
3 -5 min 20°C




20 min 20°C




Hand sanding / dry:  
P120 - P320



Machine sanding / dry:  
P120 - P320



Shelf life:  
12 Month



Store in cool place



Latex / Nitril

This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products.

Copyright: Q-Company 2017, all rights reserved.

Q-Company Int. GmbH / Beckershof 3 / D-24558 Henstedt-Ulzburg / Germany

Version: 02.01.2017