



<b>Product Name</b>	:	<b>MoTip Fine Putty</b>
<b>Article Number</b>	:	<b>000156            000157</b>
<b>Contents</b>	:	<b>250 gram            1.000 gram</b>
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>
		<b>Wolfraamweg 2</b>
		<b>NL-8471 XC WOLVEGA</b>
		<b>Telephone number    +31 561 – 69 44 00</b>
		<b>Telefax number      +31 561 – 69 44 31</b>

---

### Product description

High quality 2 component fine putty to level small irregularities in surfaces of steel, aluminium, wood, concrete and polyester.

### Product characteristics

Easy to sand  
Elastic  
Re-sprayable with all lacquer systems  
Very fine structure  
Resistant to chemicals and weather influences  
Excellent adhesion

### Physical and Chemical Characteristics

Base Putty	:	Polyester resin
Base Harder	:	Benzoyl peroxide
Density	:	1,7 Kg/dm <sup>3</sup>
Harder to be added	:	2,5%
Potlife	:	3 to 5 minutes
Layer thickness to apply	:	Up to 0,5 centimetres
Sandable after	:	approximately 30 minutes
Re-Sprayable after	:	approximately 1 hour
Heat resistant	:	To 120°C

### Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

Processing temperature 15 – 25°C.

#### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

#### Treatment

The surface should be clean, dry and free of grease. Mix the required amount of putty with the harder. Apply in the desired layer thickness.

**The drying time depends on the ambient temperature.**

After use, directly clean the tools used.

Do not store the surplus material, mixed with harder, in the can.