



DE BEER REFINISH	SATAjet® 5000 B HVLP	SATAjet® 5000 B RP®	SATAjet® 4000 B HVLP	SATAjet® 4000 B RP®	SATAjet® 3000 B HVLP	SATAjet® 3000 B RP®
1-15 Washprimer CF	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar
1-7510 Epoxyprimer white w/w	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 / 1.7 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-145 HS Surfacer w/w	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-746 High Productivity Primer w/w	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar	1.4 / 1.5 2.0 bar	1.3 / 1.4 / 1.6 1.8 - 2.0 bar
8-149 HS Tinting Surfacer w/w	1.3 2.0 bar	1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.3 1.8 - 2.0 bar
WaterBase Serie 900 or 900+	WSB / 1.3 2.0 bar	- -	WSB / 1.3 2.0 bar	- -	WSB / 1.3 2.0 bar	- -
BeroBase Serie 500	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar	WSB / 1.3 2.0 bar	1.3 1.8 - 2.0 bar
8-104 HS Clear Coat	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar	1.3 2.0 bar	1.2 / 1.3 1.8 - 2.0 bar
8-414 HS420 Clear Coat	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar
8-514 Speed Clear Coat / 8-614 Air Dry Clear Coat / 8-714 Supreme Clear Coat	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.3 / 1.4 1.8 - 2.0 bar
Beromix 2000	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar	1.3 / 1.4 2.0 bar	1.3 / 1.4 1.8 - 2.0 bar
BeroThane 3000 (HS420)	- -	1.2 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.4 1.8 - 2.0 bar	- -	1.2 / 1.4 1.8 - 2.0 bar

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.



DE BEER REFINISH	SATA [®] minijet 4400 [®] B HVLP	SATA [®] minijet 4400 [®] B RP [®]	SATAminijet [®] 3000 B HVLP	SATAjet [®] 100 B F [®] RP [®]	SATAjet [®] 100 B F [®] HVLP	SATAjet [®] 100 B P [®]
1-15 Washprimer CF	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
1-7510 Epoxyprimer white	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-145 HS Surfacer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-746 High Productivity Primer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
8-149 HS Tinting Surfacer	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.4 / 1.6 / 1.8 2.0 bar	1.4 / 1.7 / 1.9 2.0 bar	- -
WaterBase Serie 900 or 900+	0.8 SR / 1.0 SR 1.5 - 2.0 bar	- -	0.8 SR / 1.0 SR 1.5 - 2.0 bar	- -	- -	- -
BeroBase Serie 500	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.3 1.8 - 2.0 bar	-	- -
8-104 HS Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
8-414 HS420 Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
8-514 Speed Clear Coat / 8-614 Air Dry Clear Coat / 8-714 Supreme Clear Coat	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -
Beromix 2000 and 3000 Berothane (HS)	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.0 SR / 1.2 SR 2.0 bar	1.0 SR / 1.2 SR 1.5 - 2.0 bar	1.2 / 1.4 2.0 bar	- -	- -




*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.



Cromax	SATAjet® X 5500 HVLP	SATAjet® X 5500 RP®	SATAjet® 5000 B HVLP	SATAjet® 5000 B RP®	SATAjet® 4000 B HVLP	SATAjet® 4000 B RP®
Cromax® Pro Basecoat	1.2 l 0.7 bar ¹⁾	1.2 l / 1.2 O 2.0 bar	WSB / 1.3 0.7 bar ¹⁾	1.2 / 1.3 2.0 bar	WSB / 1.3 0.7 bar ¹⁾	1.2 / 1.3 2.0 bar
Cromax® Basecoat	- -	- -	WSB / 1.3 0.7 bar ¹⁾	1.2 / 1.3 2.0 bar	WSB / 1.3 0.7 bar ¹⁾	1.2 / 1.3 2.0 bar
VR1120 ValueClear VOC	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
3750S Ultra Productive VOC Clear	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
3760S Ultra Productive VOC Hi-Temp Clear	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
3800S ChromaClear® VOC	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
CC6300 VOC Protect Clear	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
CC6400 Standard VOC Clear	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
CC6600 Cromax® Pro Star Clear	- -	1.3 l / 1.3 O / 1.4 l / 1.4 O 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar	- -	1.3 / 1.4 1.8 - 2.2 bar
CC6500 High Performance VOC Clear	- -	1.2 l / 1.2 O / 1.3 l / 1.3 O 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar
CC6700 Ultra Performance Energy Clear	- -	1.2 l / 1.2 O / 1.3 l / 1.3 O 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar	- -	1.2 / 1.3 1.8 - 2.0 bar
825R Wash Primer-Surfacers / NS260x Non-Sanding Primer-Surfacers	- -	- -	1.3 / 1.4 0.7 bar ¹⁾	1.3 / 1.4 1.8 - 2.0 bar	1.3 / 1.4 0.7 bar ¹⁾	1.3 / 1.4 1.8 - 2.0 bar

¹⁾Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.



Cromax	SATA [®] minijet 4400 [®] B HVLP	SATA [®] minijet 4400 [®] B RP [®]	SATA minijet [®] 3000 B HVLP	SATA jet [®] 100 B F [®] RP [®]	SATA jet [®] 100 B F [®] HVLP	SATA jet [®] 100 B P [®]
Cromax [®] Pro Basecoat	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	- -	- -	- -
Cromax [®] Basecoat	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	- -	- -	- -
Cromax VOC Clears	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 / 1.2 1.0 - 2.0 bar	- -	- -	- -
Cromax VOC Surfacer	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	1.0 SR / 1.2 SR 1.0 - 2.0 bar	- -	- -	- -
PS106x Cromax [®] Pro Surfacer	- -	- -	- -	1.4 / 1.6 / 1.8 1.5 - 2.2 bar	1.7 / 1.9 0.7 bar ¹⁾	- -
105xR High Productive Surfacer	- -	- -	- -	1.6 / 1.8 1.5 - 2.2 bar	1.7 / 1.9 0.7 bar ¹⁾	- -
LE200x Low Emission Surfacer Plus	- -	- -	- -	1.4 / 1.6 / 1.8 1.5 - 2.2 bar	1.7 / 1.9 0.7 bar ¹⁾	- -
VR1140 ValueSurfacer VOC	- -	- -	- -	1.6 / 1.8 1.5 - 2.2 bar	1.7 / 1.9 0.7 bar ¹⁾	- -
PS108x Ultra Performance Energy Surfacer	- -	- -	- -	1.4 / 1.6 1.0 - 1.6 bar	1.4 / 1.7 0.7 bar ¹⁾	- -
PS1410 UV-A Primer-Surfacer	- -	- -	- -	1.1 1.8 - 2.0 bar	1.1 0.7 bar ¹⁾	- -
799R VOC Spray Putty	- -	- -	- -	- -	- -	P (2.5) 1.5 - 2.5 bar

¹⁾Luftdüsendruck | air cap pressure | Pression à l'intérieur du chapeau d'air

*Alle Angaben nach bestem Wissen und Gewissen aber ohne Gewähr. Bitte beachten Sie die Vorgaben des Lackherstellers. | Specifications in all conscience but without engagement. Please observe the paint manufacturer's requirements. | Toutes indications sont en notre âme et conscience mais sans garantie. Veuillez respecter les instructions du fabricant de peinture. | Todos los datos según nuestro saber y entender, pero sin garantía. Tenga en cuenta las especificaciones del fabricante de pintura.