

GENERAL INFORMATION

8-145 HS Surfacer Grey is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Sanding version.

MIXING RATIO



3 : 1 Surfacer : 2K/MS Hardener + max 10% Uni Thinner
 4 : 1 Surfacer : HS Hardener + max 15% Uni Thinner
 6 : 1 Surfacer : HS420 Hardener + max 25% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,8	2/29
HE	1,3-1,8	1,6-1,8/23-26

APPLICATION



1- 3 coat 60-180 m (2,4-7,2 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F		FORCED DRY 60°C / 140°F	
Flash off	5 - 10 minutes	Flash off	5 - 10 minutes	
Dust free	20 - 30 minutes	Dust free	-	
Dry to handle	16 hours	Dry to handle	20 - 30 minutes	
Dry to tape	16 hours	Dry to tape	20 - 30 minutes	
Dry to sand	16 hours	Dry to sand	20 - 30 minutes	
Dry to polish	-	Dry to polish	-	



SUBSTRATES



8-145 HS Surfacer Grey should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



20 - 30 minutes

COMPONENTS



47-30 2K Hardener Very Fast
 47-40 2K Hardener Fast
 47-50 2K Hardener Medium
 47-60 2K Hardener Slow
 47-35 MS Hardener Fast
 47-55 MS Hardener Medium
 47-65 MS Hardener Slow
 8-130 HS Hardener Very Fast
 8-140 HS Hardener Fast
 8-150 HS Hardener Medium
 8-160 HS Hardener Slow
 8-430 HS420 Hardener Very Fast
 8-440 HS420 Hardener Fast
 8-450 HS420 Hardener Medium
 8-460 HS420 Hardener Slow
 1-141 Uni Thinner Fast
 1-151 Uni Thinner Medium
 1-161 Uni Thinner Slow

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180–P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900+ Series
 MM 3000 - 3046 BeroThane HS420 3000 Series
 MM 500 - 5999 BeroBase 500 Series
 MM 2000 - 2099 BeroMix 2000 Series

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/IIIB(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	IIB/c. Primer - Surfacer/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	20 - 22 Dincup 4 / 20°C
	Specific Gravity (kg/L)	1,41
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	44
	Economy	7 m ² /L/60 m 285 ft ² /Gal/2,4 mil
	Gloss	Matt
	Colour	Grey

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-

GENERAL INFORMATION

8-145 HS Surfacer Grey is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Non-Sanding version.

MIXING RATIO



3 : 1 Surfacer : 2K/MS Hardener + max 20% Uni Thinner
 4 : 1 Surfacer : HS Hardener + max 30% Uni Thinner
 6 : 1 Surfacer : HS420 Hardener + max 35% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,5	2/29
HE	1,3-1,5	1,8-2,0/26-29

APPLICATION



1 coat 20 - 25 µm (0,8-1,0 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F	FORCED DRY 60°C / 140°F
Flash off	15 - 20 minutes	Flash off
Dust free	15 - 20 minutes	Dust free
Dry to handle	16 hours	Dry to handle
Dry to tape	16 hours	Dry to tape
Dry to sand	16 hours	Dry to sand
Dry to polish	-	Dry to polish

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

SUBSTRATES



8-145 HS Surfacer Grey should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



30 minutes

COMPONENTS



47-50 2K Hardener Medium
 47-60 2K Hardener Slow
 47-55 MS Hardener Medium
 47-65 MS Hardener Slow
 8-150 HS Hardener Medium
 8-160 HS Hardener Slow
 8-450 HS420 Hardener Medium
 8-460 HS420 Hardener Slow
 1-151 Uni Thinner Medium
 1-161 Uni Thinner Slow
 47-91 Spot Repair Thinner
 1-231 Fade-Out Thinner

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180—P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900[®] Series
 MM 3000 - 3046 BeroThane HS420 3000 Series
 MM 500 - 5999 BeroBase 500 Series
 MM 2000 - 2099 BeroMix 2000 Series

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/11B(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	11B/c. Primer - Surfacers/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	16 - 17 Dincup 4 / 20°C
	Specific Gravity (kg/l)	1,37
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	41
	Economy	14 m ² /L/30 µm 570 ft ² /Gal/1,2 mil
	Gloss	Matt
Colour	Grey	

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-