



<b>Product name</b>	:	<b>MoTip Industrial Lacquer</b>
<b>Article number</b>	:	<b>07000 et cetera</b>
<b>Supplier / Producer</b>	:	<b>MOTIP DUPLI B.V.</b>
		<b>Wolframweg 2</b>
		<b>NL-8471 XC WOLVEGA</b>
		<b>Telephone number</b> +31 561 – 69 44 00
		<b>Telefax number</b> +31 561 – 69 44 31

---

## Product description

High quality lacquer for professional use. To treat surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.

## Product characteristics

Fast drying  
Excellent coverage and filling property  
Lasting colour and lasting gloss  
Scratch free and shock proof  
Resistant to weather influences  
Corrosion preventive  
UV resistant and non-fading  
Good adhesion

## Physical and Chemical Characteristics

Contents	:	400 ml
Base	:	Acrylic resin
VOC-content	:	Approximately 88% w/w
Solid content	:	Approximately 12% w/w
Coverage	:	1,25 to 1,75 m <sup>2</sup>
Dust dry	:	After 5 to 10 minutes
Tack free	:	After 10 to 20 minutes
Hardened/re-sprayable	:	After 2 hours
Heat resistant	:	To 80°C

## Usage

**Before use, carefully read the directions on the packaging and act accordingly.**

### Pre Treatment

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of MoTip primer suitable for the surface. After drying, sand the base layer (grain 600).

### Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

**The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.**