

## MOTIP Heat Resistant Paint

Ord.-no.: look at ordering information

## Technical Information



Paint surfaces that are exposed to very high temperatures, such as the exhaust of your car, with MOTIP Heat Resistant Paint. Heat Resistant Paint is resistant to petrol, chemicals and weather influences.

### Quality & properties

- Heat resistant
- Excellent adhesion
- Resistant to petrol, chemicals and weather influences

### Physical & chemical data

- Base: Silicone resin
- Colourname:
  - ◊ White
  - ◊ Dark anthracite
  - ◊ Black
  - ◊ Brown
  - ◊ Anthracite
  - ◊ Beige
  - ◊ Grey
- Degree of gloss:
  - ◊ mat, 10 ±2 GU
  - ◊ semi mat, 25 ±5 GU
- Efficiency: 400 ml – 1.25 -1.75 m<sup>2</sup>
- Dry to touch: 10-15 min
- Dust dry: 5-10 min
- Completely dry: 30-60 min
- Overcoatable: 30-60 min
- Surfaces: Surfaces which are exposed to very high temperatures.
- Minimum Working Temperature: 10 °C
- Maximum Working Temperature: 25 °C
- Vapour pressure: 3500/20 bar
- Flash point: n.a.
- Storage stability: 10 years
- Content:
  - ◊ 400 ML
  - ◊ 400 ml

### How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Do not apply any primer.
- Treatment: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 10 to 25°C.
- Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.
- Apply the heat resistant lacquer in several thin layers. Before applying the next layer, again shake the aerosol. Allow to dry at room temperature for one hour. Then, heat for 30 to 60 minutes (200°C) in order to harden the paint layer. Smoke develops during the lacquer hardening process.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).
- The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

**Disposal**

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

**Marking/Labeling**

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

**As of November 24, 2021** – This release replaces all eventually earlier issued versions.

**European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim - [info-de@european-aerosols.com](mailto:info-de@european-aerosols.com)**  
**European Aerosols B.V., Wolframweg 2, NL-8471 XC Wolvega - [info-nl@european-aerosols.com](mailto:info-nl@european-aerosols.com)**