

Product Description

Hard and durable polyurethane / crosslinking acrylic enamel for interior use.
Excelent for woodwork and primed metal, where an extra tough surface is needed.

Directions for use

The substrate must be sound/stable, dry, clean, and free from all substances that may prevent good adhesion.
New wood should be primed with suitable water-borne primer. If necessary, use a suitable undercoat, followed by 2 coats of PU Enamel
Previously painted surfaces to be prepared and suitable for applying the top coat before applying the top coat. Iron and metal should be primed with suitable primer before applying the top coat.

Cleaning instructions

Cleaning with clean water, preferably added a little detergent, immediately after use.

Safety & environment

Brush / Roller: Working close, PU-gloves and protective glass.
Spray: Protective clothing, PU-gloves and shield. A2P3 mask, with air supply when needed.
Sanding: Working clothes, PU-gloves and protective glass. P2 mask with air supply when needed.
Further information and MSDS on www.bj.dk

Sprayguide

| Spraying | Nozzle | Air pressure | Ass. Air | Filter |
|-------------------------|---------------|--------------|----------|----------|
| Airless with Finefinish | 10-14 (graco) | | | 100 mesh |

Technical data

Binder: Polyurethane and crosslinking acrylic
Type:
Gloss: Approx. 50 semi-gloss
Vol. dry: App. 35%
Colours: White and Clear. Can be tinted
Drying: 2-4 hours, recoatable after approx. 12 hours at +20 °C og 65% RF
Application: +10 °C to + 25° C. RH: 40-80%
Thinning: Water
Coverage: 8-10 m²/ltr
Tools: Brush, Roller or Spraying
Mal-Code: 00-1 (1993)

